

## ITO Summary for AJA I

Date	Temp. (°C)	Ar (sccm)	O2 (sccm)	Press. (mTorr)	Power (watts DC)	Dep. Time (sec)	Dep. Time (min)	Dep. Thick (nm)	Dep. Rate (nm/min)	Sheet Resistivity (ohms/sq)	Thickness (cm)	Slice Resistivity (ohm*cm)	Sample on Optical Plot
Jul-12	20	20	N.A.	5	250	1,920	32	340	11	414,000	3.40E-05	<b>1.41E+01</b>	<b>S1</b>
8/7/2012	350	20	5	5	250	600	10	130	13	12,000	1.30E-05	<b>1.56E-01</b>	<b>S4</b>
8/7/2012	350	20	1	5	250	600	10	130	13	3,500	1.30E-05	<b>4.55E-02</b>	<b>S3</b>
8/7/2012	350	20	N.A.	5	250	600	10	130	13	30	1.30E-05	<b>3.90E-04</b>	<b>S2</b>
8/10/2012	350	20	N.A.	5	250	90	1.5	20	13	375	2.00E-06	<b>7.50E-04</b>	<b>S5</b>

