

University of Minnesota Nano Center

Prebake Dehydration Oven-Standard Operating Procedure

Badger Name: n/a

Model: Blue M Stable Therm

Location: Keller-Bay 2

Revision: 4

Revisionist: Laura Parmeter

Date: March 25, 2020

Table of contents

1. Scope
2. Tool description
3. Safety
4. Restrictions
5. Tools and Equipment
6. Procedure
 - 6.1. Setup
 - 6.2. Operating Instructions
7. Problems/Troubleshooting

University of Minnesota Nano Center

Prebake Dehydration Oven-Standard Operating Procedure

1. Scope

1.1. This document provides detailed instructions on how to properly operate the Prebake Dehydration Oven.

2. Tool description

2.1. This is a non-exhausted oven with a monitored temperature setting of 150 °C. There is a center rack for placing substrate boats. The dial is set at 150 °C.



Figure 1 The prebake dehydration oven.

3. Safety

3.1. Take caution when unloading your hot substrates when the Prebake time is complete.

University of Minnesota Nano Center

Prebake Dehydration Oven-Standard Operating Procedure

4. Restrictions

- 4.1. Wafers must not have any material on the surface that could out-gas fumes. This oven is not exhausted.
- 4.2. Do not change the temperature of this oven; it is to remain at 150 °C.

5. Tools and Equipment

- 5.1. 120V electrical outlet.
- 5.2. Quartz boat (optional)

6. Procedure

6.1. Setup

- 6.1.1. Place your substrate perpendicular in the quartz boats provided or place them on a handmade foil boat.
- 6.1.2. Users must supply their own method of timing the length of bake.

6.2. Operating Instructions

- 6.2.1. Open the door and place substrates in the oven on the rack and close the door.

7. Problems/Troubleshooting

- 7.1. If the settings are not at the above set point, notify MNC staff.